


TES 96 Coating Thickness Tester

FEATURES

- Automatic ferrous or non-ferrous substrate material measurement
- Non-magnetic coating on ferrous metal substrate and insulating coating on non-ferrous metal substrate measurement
- Audible and visual warning when tolerance limits are exceeded
- Statistical display of significant values such as mean value, standard deviation, min, max values
- Units of measurement μm /mils select
- LCD display with backlight
- Auto power off



SPECIFICATIONS

| | |
|-----------------------|---|
| Measuring Method | Electromagnetic and Eddy Current (automatic substrate recognize function) |
| Measurable Range | 0~1600 μm or 0~80.0 mils |
| Measuring Accuracy | $\pm 1 \mu\text{m}$: < 50 μm $\pm 2.5\%$: 50 μm ~ < 1000 μm $\pm 3\%$: 1000 μm < 1600 μm |
| Resolution | 0.1 μm : < 100 μm 1 μm : $\geq 100 \mu\text{m}$ |
| Data Memory | 99 points |
| Group Memory | 10 group (100 points per group) |
| Power Supply | 1.5 V alkaline batteries (size AAA) x 2 |
| Battery Life | Approx. 30 hours (with backlight off) |
| Operating Temperature | 0 to 40°C (32°F to 104°F) |
| Storage Temperature | -20 to 50°C (-40°F to 140°F) |
| Dimensions & Weight | 114 (L) x 53 (W) x 31 (H) mm / Approx. 102 g |
| Accessories | Zero calibration holder (Iron substrate, aluminum substrate), Calibration foils (Approx. 50, 100, 1000 μm), Alkaline batteries, Carrying case, Leather case, Operating manual |

TES

TES ELECTRICAL ELECTRONIC CORP.

7F, No. 31, Lane 513, Rui Guang Road, Neihu Dist. Taipei.

Taiwan, R. O. C.

Tel: (02) 2799-3660

E-Mail: tes@ms9.hinet.net

Fax: 886-2-2799-5099

http://www.tes.com.tw

شرکت صائن

WWW.SAENCO.COM

021 88936611

